



# VG 66

## PREMIUM VARNISH

The ultimate high gloss, elastic and durable tung and linseed oil varnish.

For best results on bare timber apply two coats of BRAVA IMPREGANTE or BRAVA VG 61 DEFENDER by brush first.

A minimum of 6 total coats of VG 66 PREMIUM VARNISH are to be applied in total, making sure the first coat is diluted 40% with white spirit, then reducing dilution after each coat, and applying the final two coats undiluted.

'Denibbing' using P320 paper between each coat is recommended.

For previously coated timber two coats of undiluted VG 66 PREMIUM VARNISH should be applied after a light rub down using P320 paper.

The surface must be clean, dry and free from any dust prior to application.

Stir the product gently and slowly before the application.

When painting in the open-air, the coat must be dry before nightfa



thinner:	white spirit"
coverage:	18 MQ/LT
touch drying:	8h
overcoating:	24 h.
viscosity:	120 sec. (Ford)
suggested n° coats:	4/6
dry film thickness:	150 microns
solids content:	60%
flash point:	37° C.
specific weight:	0,9
airless:	30/1 - 0.017 - 0.019
spry:	2 - 3 Kg/cm <sup>2</sup> - 1.2 - 1.4

### AVAILABLE:

glossy 750 ml tin

#### U.K. Importer:



MARINE & INDUSTRIAL LLP,  
Station Road, Worstead, North Walsham, NR28 9RZ.  
Tel: 01692 406822. Fax: 01692 406866.  
sales@marineindustrial.co.uk

