



SEAJET 118 ULTRA-BUILD EPOXY PRIMER

SEAJET 118 ULTRA-BUILD EPOXY PRIMER provides a high build, abrasion resistant anticorrosive barrier coat for all surfaces. It is also tolerant to a surface which cannot be prepared to the highest standard.

Characteristics:

- Compared to other primers, a reduced number of coats will achieve the specified thickness.
- Protection against gel-coat osmosis blistering below water.
- An ideal primer for fibre-glass, metal keels and above water areas.

TECHNICAL DATA

Type	Modified epoxy, ultra build primer
Recommended use	- Protection of all surfaces of yachts and pleasure crafts for above and below water. - Effective prevention of gel-coat osmosis blistering below water.
Surface Preparation	Degrease and clean using THINNER E wiping to remove all contamination. Bare fibreglass: Abrade using P180-240 abrasive paper followed by final cleaning. Apply a single coat of SEAJET 118 (or 2 coats for osmosis protection). Bare aluminium: Apply one coat of SEAJET 017, 3-4 coats of SEAJET 118. Steel hulls and metal keels: Sand blast to SA 2½ or hand prepare bare areas. Apply 3-4 coats to achieve the required minimum film thickness of 250 microns. Before application of antifouling or topcoat, apply a tie coat of SEAJET 011 for underwater areas or SEAJET 012 Universal Primer/Undercoat for above water areas.

Physical Data (Mix)	Colour: Silver
	Flash point: 32°C
	Volume solids %: 89 ±2
	VOC (Theoretical): 158 g/l.

Application Details	Mixing ratio: Base: 88 Hardener: 12 (by volume)
	Thinner: SEAJET THINNER E
	Application Data: Airless spray, brush, roller*
	Add the hardener to the base whilst mixing. Stir well before use.
	Min. Temperature: 10 °C
	Max. humidity: 85% R.H.

Spray Details	Tip No.: GRACO 619, 621
	Paint output pressure: 14.7 - 17.7 MPa
	Thinning: 0 - 5% (by volume)

Film thickness and spreading rate:	Min.	Max.	
	Film Thickness, wet: 112	281	µm
	Film Thickness, dry: 100	250	µm
	Spreading Rate: 8,9	3,6	m²/l (theoretical)

Preferable preceding coating	-
-------------------------------------	---

Preferable subsequent coating	SEAJET 011 Underwater Primer, within 48 hours. For above water, SEAJET 012 Universal Primer/Undercoat
--------------------------------------	--

Packing	Two Pack Product
----------------	------------------

Notes	*Film thickness and spreading rate depends on application method.
--------------	---


Coating data

Temperature	Drying time (at DFT 200 μ)	Overcoating interval (at DFT 200 μ)	Induction time	Pot life	Dry to launch	Remarks
-5 °C	-	-	-	-	-	-
0 °C	-	-	-	-	-	-
5 °C	-	-	-	-	-	-
10 °C	Surface dry: 12 hours Hard dry 24 hours	Min.: 32 hours Max.: 7 days*	-	3 hours	-	-
20 °C	Surface dry: 6 hours Hard dry 12 hours	Min.: 20 hours Max.: 7 days*	-	2 hours	-	-
30 °C	Surface dry: 4 hours Hard dry 8 hours	Min.: 16 hours Max.: 5 days*	-	1 hour	-	-

* = overcoating with SEAJET 118, please consult CMP for overcoating with other products.

Note: Drying times and overcoating intervals will increase with increasing film thickness applied.

Before re-coating, always check that the existing paint film is 'through' dry.

Safety information: If Health, Safety and Environmental information is required a Health and Safety Data Sheet can be obtained from Chugoku Paints B.V.

Personal Protection advice and additional information can be obtained from the product Health and Safety Data Sheet which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

Definitions:		
Tolerances:		The numerical information quoted in this Technical Data Sheet is subject to normal manufacturing tolerances.
Spreading Rate:		The spreading rate can vary depending on application conditions, the geometrical complexity of the structure, the weather conditions, etc.
Volume Solids:		The volume solids figure given in this Technical Data Sheet is the percentage of dry film obtained from a given wet film thickness under specified application rate and conditions measured by the Chugoku Standard Method corresponding to ASTM method D2697.
Overcoating Intervals:		The intervals given assume preparation consistent with good painting
Hard dry:		The time taken until the product can be walked on without damaging it. Time taken until full mechanical strength is obtained is longer.
V.O.C.:		Theoretical quantity of volatile organic compounds in g/l.

Disclaimer: Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam.

The Inspector will undertake to the best of their ability, to carry out assistance during application of the products delivered by Chugoku, by only rendering advice in connection with the application at site. The Inspector undertakes to carry out the project in a conscientious manner, but Chugoku and/or the Inspector will not accept any kind of liability, direct or indirect, if the project does not give the results expected. Under all circumstances, the Buyer remains responsible for the execution of the project. Any advice and/or assistance rendered by the Inspector will be subject to such (final) responsibility of the buyer, and moreover subject to the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. Even when damages or delays have been caused by faults or negligence on the side of Chugoku and/or the Inspector, such will not result in any liability whatsoever of Chugoku or the Inspector. Liability of both Chugoku or the Inspector for any consequential damages is explicitly excluded.

Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.