

# PRODUCT DATA SHEET

## Sika® Sanisil®

ACETOXY SILICONE SEALANT FOR SANITARY APPLICATIONS



### DESCRIPTION

Sika® Sanisil® is a 1-component, solvent-free sealant with resistance to fungus. Suitable for use in hot and tropical climatic conditions.

### USES

Sika® Sanisil® is designed for sanitary or other sealing applications where mildew resistance is required.

### CHARACTERISTICS / ADVANTAGES

- High elasticity and flexibility
- Long term fungus and mildew resistance
- Very good UV and weathering resistance

### SUSTAINABILITY

Sika® Sanisil® conforms to LEED® v3 IEQ 4.1

- VOC content < 50 g/L (US EPA method 24)

### APPROVALS / CERTIFICATES

- EN 15651-1 F EXT-INT CC
- EN 15651-3 S

### PRODUCT INFORMATION

<b>Composition</b>	Acetoxy silicone
<b>Packaging</b>	300 mL cartridges, 12 cartridges per box
<b>Colour</b>	Clear, white, brown, beige and grey
<b>Shelf life</b>	Sika® Sanisil® has a shelf life of 12 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
<b>Storage conditions</b>	Sika® Sanisil® shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
<b>Density</b>	~1.00 kg/L (ISO 1183-1)

### TECHNICAL INFORMATION

<b>Shore A Hardness</b>	~20 (28 d)	(ISO 868)
<b>Tensile Strength</b>	~1.7 N/mm <sup>2</sup>	(ISO 8339)
<b>Secant Tensile Modulus</b>	~0.35 N/mm <sup>2</sup> at 100% elongation (after 28 d at 23 °C)	(ISO 8339)
<b>Elongation at Break</b>	~790 %	(ISO 37)

<b>Elastic Recovery</b>	> 90 %	(ISO 7389)
<b>Tear Propagation Resistance</b>	~1.8 N/mm	(ISO 34)
<b>Movement Capability</b>	± 20 %	(ISO 9047)
<b>Service Temperature</b>	-40 °C min. / +100 °C max.	
<b>Joint Design</b>	The joint width must be designed to suit the joint movement required and the movement capability of the sealant. For joints ≥ 10 mm and ≤ 20 mm wide, a joint depth of 10 mm is recommended. For larger joints please contact our Technical Department.	

## APPLICATION INFORMATION

Consumption	Joint length [m] per 300 mL	Joint width [mm]	Joint depth [mm]
	3	10	10
2	15	10	
1.5	20	10	

  

<b>Sag Flow</b>	< 1 mm (20 mm profile, 23 °C)	(ISO 7390)
<b>Ambient Air Temperature</b>	+5 °C min. / +40 °C max. (min. 3 °C above dew point temperature)	
<b>Substrate Temperature</b>	+5 °C min. / +40 °C max.	
<b>Curing Rate</b>	~3.0 mm/24 h (23 °C / 50% r.h.)	(CQP 049-2)
<b>Skinning time</b>	~15 min (23 °C / 50% r.h.)	(CQP 019-1)

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sika® Sanisil® adheres without primers and/or activators. However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed:

Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. Before sealing, allow a flash-off time of > 15 minutes (< 2 hours). Other metals, such as copper, brass and titanium-zinc, also have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of > 30 minutes (< 4 hours) before sealing the joints. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a flash-off time of > 30 minutes (< 4 hours). Glass shall be cleaned with isopropyl alcohol before application.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.  
For more detailed advice and instructions please contact our Technical Department.

### APPLICATION METHOD / TOOLS

Sika® Sanisil® is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a cartridge into the sealant gun and extrude Sika® Sanisil® into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sika® Sanisil® sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time.  
Do not use tooling products containing solvents.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically.

## FURTHER INFORMATION

Safety Data Sheet  
Pre-treatment Chart Sealing and Bonding

## IMPORTANT CONSIDERATIONS

- Do not use Sika® Sanisil® on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use in totally confined spaces, Sika® Sanisil® requires atmospheric moisture to cure.
- Sika® Sanisil® is not recommended for porous substrates, such as concrete, stone, marble and granite. Bleeding can occur when Sika® Sanisil® is used on these substrates.
- Sika® Sanisil® is not recommended for use on submerged joints, joints where physical abuse or abrasion are likely to occur, structural glazing or insulated glazing, and food contact applications.
- Do not use Sika® Sanisil® for medical or pharmaceutical uses.
- Acetic acid released during the curing of Sika® Sanisil® can cause the corrosion of mirror silver and sensitive metals such as cooper, brass and lead.
- Do not use Sika® Sanisil® on alkaline surfaces such as concrete, plaster and brick.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

SikaSanisil-en-AE-(03-2018)-1-1.pdf

Product Data Sheet

Sika® Sanisil®

March 2018, Version 01.01

020514030000000011

